



SUNRISE

ENVIRONMENTAL SCIENTIFIC

Blending the Demands of Industry and Environment

THRUSTER

RUST NEUTRALIZING COMPOUND

NEUTRALIZADOR DE ÓXIDO

**READ ENTIRE LABEL BEFORE USING.
KEEP OUT OF REACH OF CHILDREN**

SAFETY SECTION

SCAN FOR
SDS & INFO



TOXICITY 1

FIRE 0

REACTIVITY 0

SPECIAL NA



DANGER

**SKIN AND EYE IRRITANT
RESPIRATORY TRACT IRRITANT
SWALLOWING WILL CAUSE GASTRO-
INTESTINAL IRRITATION**



Gloves, apron and goggles recommended. Do not ingest. If ingested drink large quantities of potable water. Do not induce vomiting. Never give anything by mouth to an unconscious person. Use ventilation adequate to prevent; cough, hoarseness, or irritation. OSHA approved respirator recommended. If eyes are contacted, flush with water for at least 15 minutes. See a physician immediately. If skin is contacted, wash off with soap and water. Do not apply ointments until a physician is consulted. Clothing that is contaminated should be removed immediately. Flush with large amounts of water. Wash in an automatic machine before wearing again. Dispose of empty container in accordance with local regulations. Consult Safety Data Sheet for additional information.

Ingredient Name	CAS#
Glycol Ether EB	111-76-2



WARNING: This product can expose you to chemicals including Isobutyl Methyl Ketone, which is known to the State of California to cause cancer and/or cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

PRODUCT #5041 • BATCH #

TO REORDER CALL US @ 800.648.1153

THRUSTER

THRUSTER chemically neutralizes rust and leaves a long-term preventative coating in its place. THRUSTER seals, protects and extends the life of ferrous metal. The application of this compound turns the rusted area into a black protective finish. After curing, the affected area may be painted if desired.

DIRECTIONS: Clean area to be treated by removing all grease, oil, loose and powdered rust. Remove loose rust from surface with a wire brush. Rinse with clean water. Product may be applied while surface is still damp. Shake container well, then spray, brush or roll on product until entire surface is covered. Let dry. If small pin holes appear in black film, re-brush with a wire brush and apply a second coat. Rinse all application equipment with water before the polymer dries and hardens. Apply when surface temperature is between 50°F and 90°F.

SHIPPING/ DOT CLASSIFICATION

LIMITED QUANTITY

SUNRISE ENVIRONMENTAL SCIENTIFIC

**800-648-1153 SUNRISENV.COM
PO BOX 10207 - RENO, NEVADA 89510**

